

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions and listings of claims in the application:

1. (Previously presented) A cocoon-shaped colloidal silica that does not dissolve in an aqueous alkali solution of a pH of 11.5 or less and more than 11.
2. (Previously presented) A cocoon-shaped colloidal silica prepared from hydrolyzing an alkoxysilane condensate in the presence of an ammonia or ammonium salt catalyst.
3. (Currently amended) A cocoon-shaped colloidal silica prepared by further heating under pressure ~~[[the]]~~ a colloidal silica prepared by hydrolyzing an alkoxysilane condensate in the presence of an ammonia or ammonium salt catalyst.
4. (Previously presented) A cocoon-shaped colloidal silica as set forth in Claim 3, wherein the temperature to which said colloidal silica is heated under pressure is 105 to 374.1 °C.
5. (Currently amended) A cocoon-shaped colloidal silica as set forth in Claim 2 or 3, wherein said alkoxysilane condensate has an average degree of condensation of 2 to 8.
6. (Currently amended) Polishing abrasive particles comprising the cocoon-shaped colloidal silica as set forth in any one of ~~[[the]]~~ Claims 1 to ~~[[5]]~~3.
7. (Previously presented) A process for manufacture of a cocoon-shaped colloidal silica, the process comprising adding continuously an alkoxysilane condensate or its solution in an aqueous solvent to an aqueous solution of ammonia or an

ammonium salt or to an aqueous solution containing ammonia or an ammonium salt and an aqueous solvent, thereby hydrolyzing the alkoxysilane.

8. (Currently amended) A process for the manufacture of a cocoon-shaped colloidal silica, the process comprising adding continuously an alkoxysilane condensate or its solution in an aqueous solvent to an aqueous solution of ammonia or an ammonium salt or to an aqueous solution containing ammonia or an ammonium salt and an aqueous solvent, thereby hydrolyzing the alkoxysilane; and further heating under pressure.

9. (Previously presented) A process for the manufacture of a cocoon-shaped colloidal silica set forth in Claim 8, wherein the temperature to which said alkoxysilane condensate hydrolyzate is heated under pressure is 105 to 374.1°C.

10. (Currently amended) A process for the manufacture of a cocoon-shaped colloidal silica as set forth in ~~any one of the Claims~~ Claim 7 to Claim 9 or 8 wherein said alkoxysilane condensate has an average degree of condensation of 2 to 8.